

Slip Resistance Ratings



		Chemical Resistance	Slip Resistance		Slip Resistance - Untreated	Slip Resistance - Treated
		ISO 10545-13	ASTM C-1028	DIN 51130	AS/NZS 3661.1	AS/NZS 3661.1
Stocked in 3m x 1m	Blend	No visible effect	$\mu > 0,6$	R9	$\mu = 0.21$	$\mu > 0.4$
	Collection	No visible effect	$\mu > 0,6$	R9	$\mu = 0.21$	$\mu > 0.4$
	Filo	Partial change in surface appearance		R9	$\mu = 0.21$	N/A
	Naturali	No visible effect	$\mu > 0,6$	R9	$\mu = 0.21$	$\mu > 0.4$
	Oxide	No visible effect	$\mu > 0,6$	R10	$\mu = 0.26$	$\mu > 0.4$

Note: Laminam Filo range is not recommended for horizontal applications such as flooring, as the heavily textured surface may require more cleaning. It is also not possible to treat the surface of Filo range to increase the slip resistance.

Laminex[®]
New Zealand

www.laminam.co.nz